CHOKSI PIGMENTS

Full Strength Reduction 1:10

	APPLICATIONS											
	Printing Inks					Paints			Plastics			
	Offset		Flexo/Liquid									
	Heat Set	Cold Set	Water Based	Solvent Based	NC Based	Air Drying	Stoving	Water Based	Plastics	PVC	Rubber	Textile Emulsion
PHTHALOCYANINE GREEN G Pigment Green 36 C.I. No. 74265	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y

Y = Recommended; N = Not Recommended

			FASTNESS PROPERTIES						PHYSICAL AND CHEMICAL PROPERTIES																
			Light (1 ÿ 8) Scale		Heat (1 ÿ 5) Scale		Overspray (1 ÿ 5) Scale		Reagents (1 ÿ 5) Scale			Solvents (1 ÿ 5) Scale								Plasticizers / Oils (1 ÿ 5) Scale					
Specific Gravity	Bulk Volume	Oil Absorption gm / 100 gm	Full Strength	Reduction Tone	150°C / 20 Min.	180°C / 10 Min.	120°C / 30 Min.	N. C. Lacquer	Water	5% Acid HCL	5% Alkali NaOH	Ethanol	N-Butanol	N-Butyl Acetate	M.E.K.	White Spirit	Xylene	Mixed NC Solvents	DEG	D.B.P.	D.O.P.	Linseed Oil	Oleic Acid	Soap	Paraffin Wax
1.6	2	42 ± 2	7	6	6	6	6	4	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5