



Full Strength Reduction 1:10



LAKE RED C (Opaque)
Pigment Red 53:1
C.I. No. 15585:1

APPLICATIONS											
Printing Inks					Paints			Plastics			
Offset		Flexo/Liquid			Air Drying	Stoving	Water Based	Plastics	PVC	Rubber	Textile Emulsion
Heat Set	Cold Set	Water Based	Solvent Based	NC Based							
Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	N

Y = Recommended; N = Not Recommended

Specific Gravity	Bulk Volume	Oil Absorption gm / 100 gm	FASTNESS PROPERTIES					PHYSICAL AND CHEMICAL PROPERTIES																	
			Light (1 ÷ 8) Scale	Heat (1 ÷ 5) Scale	Overspray (1 ÷ 5) Scale	Reagents (1 ÷ 5) Scale			Solvents (1 ÷ 5) Scale					Plasticizers / Oils (1 ÷ 5) Scale											
						Full Strength	Reduction Tone	150°C / 20 Min.	180°C / 10 Min.	120°C / 30 Min.	N. C. Lacquer	Water	5% Acid HCL	5% Alkali NaOH	Ethanol	N-Butanol	N-Butyl Acetate	M.E.K.	White Spirit	Xylene	Mixed NC Solvents	DEG	D.B.P.	D.O.P.	Linseed Oil
1.8	3.5	50 + 2	5	2	4	4	2	2	5	3	2	4	2	2	2	4	2	1	2	3	3	5	4	1-2	4