CHOKSI PIGMENTS

Full Strength Reduction 1:10

	APPLICATIONS															FASTNESS PROPERTIES						PHYSICAL AND CHEMICAL PROPERTIES																
	Printing Inks					Paints			Plastics							Light (1 ÿ 8) Scale		Heat (1 ÿ 5) Scale		Overspray (1 ÿ 5) Scale		Reagents (1 ÿ 5) Scale			Solvents (1 ÿ 5) Scale								Plasticizers / Oils (1 ÿ 5) Scale					
	Offset		Flexo/Liquid																																			
	Heat Set	Cold Set	Water Based	Solvent Based	NC Based	Air Drying	Stoving	Water Based	Plastics	PVC	Rubber	Textile Emulsion	Specific Gravity	Bulk Volume	Oil Absorption gm / 100 gm	Full Strength	Reduction Tone	150°C / 20 Min.	180°C / 10 Min.	120°C / 30 Min.	N. C. Lacquer	Water	5% Acid HCL	5% Alkali NaOH	Ethanol	N-Butanol	N-Butyl Acetate	M.E.K.	White Spirit	Xylene	Mixed NC Solvents	DEG	D.B.P.	D.O.P.	Linseed Oil	Oleic Acid	Soap	Paraffin Wax
YELLOW AGG Pigment Yellow 14 C.I. No. 21095	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	1.4	4	40 ± 2	5-6	3	5	4	4	2	5	5	5	5	4	4	3	5	3	3	5	5	5	5	5	5	5

Y = Recommended; N = Not Recommended