



Full Strength Reduction 1:10



RUBIN TONER CAT (Transparent)
Pigment Red 57
C.I. No. 15850

APPLICATIONS											
Printing Inks			Paints			Plastics					
Heat Set	Cold Set	Water Based	Solvent Based	NC Based	Air Drying	Stoving	Water Based	Plastics	PVC	Rubber	Textile Emulsion
N	N	Y	Y	Y	Y	Y	Y	Y	Y	Y	N

Y = Recommended; N = Not Recommended

		FASTNESS PROPERTIES							PHYSICAL AND CHEMICAL PROPERTIES																
Specific Gravity	Bulk Volume	Oil Absorption gm / 100 gm	Light (1 ÷ 8) Scale	Heat (1 ÷ 5) Scale	Overspray (1 ÷ 5) Scale	Reagents (1 ÷ 5) Scale		Solvents (1 ÷ 5) Scale			Plasticizers / Oils (1 ÷ 5) Scale														
			Full Strength	Reduction Tone	150°C / 20 Min.	180°C / 10 Min.	120°C / 30 Min.	N. C. Lacquer	Water	5% Acid HCL	5% Alkali NaOH	Ethanol	N-Butanol	N-Butyl Acetate	M.E.K.	White Spirit	Xylene	Mixed NC Solvents	DEG	D.B.P.	D.O.P.	Linseed Oil	Oleic Acid	Soap	Paraffin Wax
1.55	3.5	50	5-6	3	4	3	2	2	5	2	2	4	1	2	1	5	3	2	2	4	4	5	4	1	4